

Seite 1 von 14 Prüfbericht-Nr.: Auftrags-Nr.: 190105940 60358333 001 Order No .: Test Report No.: Page 1 of 14 Kunden-Referenz-Nr.: Auftragsdatum: 2019-11-29 N/A Client Reference No.: Order date: Xinxiang Huaxi Sanitary Materials Co.,Ltd. Auftraggeber: Client: Dingluan Industrial Zone, Changyuan, Xinxiang 453400 Henan Province, China Prüfgegenstand: Disposable Surgical Face Mask Test item: Bezeichnung / Typ-Nr.: **Elastic Earloop Type** Identification / Type No.: Auftrags-Inhalt: Type test Order content: Prüfgrundlage: EN 14683:2019+AC:2019 Test specification: Wareneingangsdatum: 2020-02-12 Date of receipt: Prüfmuster-Nr.: **Engineering sample** Test sample No .: Prüfzeitraum: 2020-02-13 to 2020-03-25 Testing period: Ort der Prüfung: See page 3 Place of testing: Prüflaboratorium: TÜV Rheinland (China) Ltd. Testing laboratory: Prüfergebnis\*: **Pass** Test result\*: geprüft von I tested by: kontrolliert von I reviewed by: 2020-03-26 Project Engineer 2020-03-26 Rev Datum Datum Name / Stellung Unterschrift Name / Stellung Unterschrift Date Name | Position Signature Date Name / Position Signature Sonstiges I Other.

Zustand des Prüfgegenstandes bei Anlieferung: Prüfmuster vollständig und unbeschädigt Condition of the test item at delivery: Test item complete and undamaged Legende: 1 = sehr gut 2 = gut 3 = befriedigend 4 = ausreichend 5 = mangelhaft P(ass) = entspricht o.g. Prüfgrundlage(n) F(ail) = entspricht nicht o.g. Prüfgrundlage(n) N/A = nicht anwendbar N/T = nicht getestet 3 = satisfactory Legend: 1 = very good 2 = good4 = sufficient 5 = poorP(ass) = passed a.m. test specification(s) F(ail) = failed a.m. test specification(s) N/A = not applicable N/T = not tested

Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.

This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be

duplicated in extracts. This test report does not entitle to carry any test mark.

EN 14683:2019+AC: 2019
Medical face masks —
Requirements and test methods

Total number of pages .....: See cover page

Testing Laboratory .....: TÜV Rheinland (China) Ltd.

Address...... Unit 707, AVIC Building, No. 10B, Central Road, East 3rd Ring

Road, Chaoyang District, Beijing 100022, P,R,China

Applicant's name .....: Xinxiang Huaxi Sanitary Materials Co., Ltd.

Address...... Dingluan Industrial Zone, Changyuan, Xinxiang 453400 Henan

Province, China

Test specification:

Standard .....: EN 14683:2019+AC:2019

Test procedure ...... Type test

Non-standard test method.....: N/A

Test Report Form No. .....: EN 14683:2019+AC:2019\_A

Test Report Form Originator .....: TÜV Rh (SZ)

Master TRF .....: 2020-03

Test item description.....: Disposable Medical Face Mask

Trade Mark.....: N/A

Manufacturer .....: Xinxiang Huaxi Sanitary Materials Co., Ltd.

Dingluan Industrial Zone, Changyuan, Xinxiang 453400 Henan

Effective date: 2020-03-12

Province, China

Model/Type reference.....:

Elastic Earloop Type

Classification.....: Type IIR

Page 3 of 14

Report No. 60358333 001

None	
Summary of testing:	
Tests performed (name of test and test clause):	Testing location:
Clause 5.1.1 Materials and construction	TÜV Rheinland (China) Ltd.
Clause 5.1.2 Design	Unit 707, AVIC Building, No. 10B, Central Road, East 3rd Ring Road, Chaoyang District, Beijing 100022, P,R,China
Clause 5.2.2: Bacterial filtration efficiency (BFE) Clause 5.2.3: Breathability	ShenZhen Academy of Metrology & Quality Inspection
Clause 5.2.4: Splash resistance	Longhua Experimental Base: No.114,
	Minkang North Road, Minzhi Avenue, Longhua District, Shenzhen
Note: All tests listed as above have been conducted in the competent external lab under the supervision of a TUV engineer	
Clause 5.2.5: Microbial cleanliness (Bioburden)	CCIC Huatongwei international inspection (Suzhou) Co., Ltd
	Room 101, Building G, Ruoshui Road 388, Suzhou, Jiangsu, China



# Copy of marking plate

The artwork below may be only a draft.


#### Label:



### Box:











Page 7 of 14

Report No. 60358333 001

Date of receipt of test item(s)	See cover nage
Date of receipt of test item(s)	See cover page
Possible test case verdicts:	
- test case does not apply to the test object:	N/A
- test object does meet the requirement:	P (Pass)
- test object was not evaluated for the requirement:	N/E (collateral standards only)
- test object does not meet the requirement:	F (Fail)
General remarks:  "(See Attachment #)" refers to additional information a "(See appended table)" refers to a table appended to The tests results presented in this report relate only to This report shall not be reproduced except in full without List of test equipment must be kept on file and available Additional test data and/or information provided in the Throughout this report a □ comma / □ point is a Name and address of factory (ies)	the report. the object tested. but the written approval of the testing laboratory. ble for review. attachments to this report.  sed as the decimal separator.
General product information:	
The submitted samples are type IIR, Disposable Medic protect against the spread or transmission of infectiou theatres and other medical facilities. The main aim is non-sterile product.  The test results are for reference only. Relevant certific sold in Europe.	is germs during surgical interventions in operating to protect the patient against infectious germs. It is a

Revision number: 1.0

	EN 14683:2019+AC:20		
Clause	Requirement + Test	Result - Remark	Verdict
4	Classification		Р
	Medical face masks specified in this European Standard are classified into two types (Type I and Type II) according to bacterial filtration efficiency whereby Type II is further divided according to whether or not the mask is splash resistant. The 'R' signifies splash resistance.	Type IIR	P
5	Requirements		Р
5.1	General		Р
5.1.1	Materials and construction		P
	The medical face mask is a medical device, generally composed of a filter layer that is placed, bonded or moulded between layers of fabric.	Polypropylene, Polyester fiber, Spandex	P
	The medical face mask shall not disintegrate, split or tear during intended use.	Complied	Р
141	In the selection of the filter and layer materials, attention shall be paid to cleanliness.	Complied	Р
5.1.2	Design		P
	The medical face mask shall have a means by which it can be fitted closely over the nose, mouth and chin of the wearer and which ensures that the mask fits closely at the sides.	Fitted closely over nose.	Р
	Medical face masks may have different shapes and constructions as well as additional features such as a face shield (to protect the wearer against splashes and droplets) with or without anti-fog function, or a nose bridge (to enhance fit by conforming to the nose contours).	With nose clip.	P
5.2	Performance requirements		Р
5.2.1	General		Р
****	All tests shall be carried out on finished products or samples cut from finished products.		Р
5.2.2	Bacterial filtration efficiency (BFE)		Р
	When tested in accordance with Annex B, the BFE of the medical face mask shall conform to the minimum value given for the relevant type in Table 1.1 1.2.	The Bacterial Filtration Efficiency ≥ 98% See appended Table 5.2.2	Р
	For thick and rigid masks such as rigid duckbill or cup masks the test method may not be suitable as a proper seal cannot be maintained in the cascade impactor. In these cases, another valid equivalent method shall be used to determine the BFE.	Not such masks	N/A

	EN 14683:2019+AC:20	19	
Clause	Requirement + Test	Result - Remark	Verdict
	When a mask consists of two or more areas with different characteristics or different layer-composition, each panel or area shall be tested individually.		N/A
	The lowest performing panel or area shall determine the BFE value of the complete mask		N/A
5.2.3	Breathability		Р
	When tested in accordance with Annex C, the differential pressure of the medical face mask shall conform to the value given for the relevant type in Table 2.1 2.2.	The differential pressure <60 Pa/cm² See appended Table 5.2.3	P
	If the use of a respiratory protective device as face mask is required in an operating theatre and/or other medical settings, it might not fulfil the performance requirements with regard to differential pressure as defined in this European Standard. In such case, the device should fulfil the requirement as specified in the relevant Personal Protective Equipment (PPE) standard(s).	No such respiratory protective device provided	N/A
5.2.4	Splash resistance		P
	When tested in accordance with ISO 22609:2004 the resistance of the medical face mask to penetration of splashes of liquid shall conform to the minimum value given for Type IIR in Table 1.	See appended Table 5.2.4	Р
5.2.5	Microbial cleanliness (Bioburden)		Р
	When tested according to EN ISO 11737-1:2018 the bioburden of the medical mask shall be ≤ 30 CFU/g tested (see Table 3.1 3.2).	The bioburden of the medical mask was ≤30 CFU/g See appended Table 5.2.5	P .
5.2.6	Biocompatibility		Р
	According to the definition and classification in EN ISO 10993-1:2009, a medical face mask is a surface device with limited contact.	The biocompatibility of mask was evaluated in following report: CSTBR20030060 CSTBR20030061 CSTBR20030062	Р
	The manufacturer shall complete the evaluation of the medical face mask according to EN ISO 10993-1:2009 and determine the applicable toxicology testing regime.	The biocompatibility of mask was evaluated in following report: CSTBR20030060 CSTBR20030061 CSTBR20030062	Р
	The results of testing should be documented according to the applicable parts of the EN ISO 10993 series.	The biocompatibility of mask was evaluated in following report: CSTBR20030060 CSTBR20030061 CSTBR20030062	Р

	EN 14683:2019+AC:20	19		
Clause	Requirement + Test	Result - Remark	Verdict	
	The test results shall be available upon request.	The biocompatibility of mask was evaluated in following report: CSTBR20030060 CSTBR20030061 CSTBR20030062	Р	
6	Marking, labelling and packaging		Р	
	Annex I, §13, of the Medical Devices Directive (93/42/EEC) or Annex I, §23, of the Medical Device	Considered	Р	
· ·	Regulation (EU) 2017/745 specifies the information that should be specified on the packaging in which the medical face mask is supplied.			
	The following information shall be supplied:		Р	
	a) number of this European Standard;	EN 14683 Marked on the label	Р	
	b) type of mask (as indicated in Table 1).	Type IIR Marked on the label	Р	
	EN ISO 15223-1:2016 and EN 1041:2008+A1:2013 should be considered.	Compliance	Р	

		EN 14683:2019+AC:201	9	
Clause	Requirement + Test		Result - Remark	Verdict

5.2.2	TABL	TABLE: Bacterial filtration efficiency (BFE)						
Batch/ lot no.:	Test Speci -men no.:	Dimension of the test specimen L x W (mm x mm)	test area (cm²)	Flow rate (I/min)	Mean of the total plate counts of the two positive controls	Mean plate count of the negative controls	BFE for each test specimen (%)	Remarks
2006090 6	1	100×100	100	28.3	2419	0	99.0	≥98
	2	100×100	100	28.3	2367	0	99.0	≥98
,	3	100×100	100	28.3	2366	. 0	98.0	≥98
	4	100×100	100	28.3	2412	0	99.0	≥98
	5	100×100	100	28.3	2389	0	98.0	≥98

Supplementary information: 1, Each specimen was conditioned at  $(21 \pm 5)^{\circ}$ C and  $(85 \pm 5)\%$  relative humidity for 4h to bring them into equilibrium with atmosphere prior to testing.

2, The side of the test specimen was facing towards the challenge aerosol:out side of mask

		EN 14683:2019+AC:201	9	
Clause	Requirement + Test		Result - Remark	Verdict

5.2.3	TABLE: Breathability (Differential pressure)						
Batch/ lot no.:	Test Specimen number- Test area number	Differential pressure for each test area (Pa/cm²)	The averaged differential pressure for each test specimen (Pa/cm²)	Flow rate (I/min)	Remarks		
200609	1-1	28.2	28.0	8	<60		
96	1-2	27.8		8 .	<60		
	1-3	28.0		8	<60		
	1-4	27.9		8	<60		
	1-5	28.1		8	<60		
	2-1	36.7	36.9	8	<60		
	2-2	36.9		8	<60		
	2-3	37.0		8	<60		
	2-4	36.8		8	<60		
	2-5	37.1		8	<60		
<b>+</b>	3-1	30.5	30.7	8	<60		
	3-2	30.9		8	<60		
	3-3	30.6		8	<60		
	3-4	30.8		8	<60		
	3-5	30.7		8	<60		
	4-1	31.6	31.9	8	<60		
	4-2	31.7		8	<60		
	4-3	32.1		8	<60		
	4-4	32.3		8	<60		
	4-5	31.8		8	<60		
	5-1	32.7	32.5	8	<60		
	5-2	32.6		8	<60		
	5-3	32.4		8	<60		
	5-4	32.7		8	<60		
	5-5	32.1		8	<60		

# **Supplementary information:**

Each specimen was conditioned at (21  $\pm$  5) °C and (85  $\pm$  5) % relative humidity for 4h to bring them into equilibrium with atmosphere prior to testing.

			EN 14683:2019+AC:2019		
Clause	Red	quirement + Test	Result - Re	mark	Verdict
5.2.4	ТА	TABLE: Splash resistance			Р
Batch/ lo	SERVICE CONTRACTOR	V basedagnes resouvered commission (1990) Visco (1990)	The material of tested mask	Test result (Pass/fail)	Remarks
20060906	<b>3</b>	1	Polypropylene, Polyester fiber, Spander	c, Pass	-
		2	Polypropylene, Polyester fiber, Spander	c, Pass	-
		3	Polypropylene, Polyester fiber, Spander	c, Pass	-
		4	Polypropylene, Polyester fiber, Spander	c, Pass	-
		5	Polypropylene, Polyester fiber, Spander	c, Pass	-
		6	Polypropylene, Polyester fiber, Spander	c, Pass	-
		7	Polypropylene, Polyester fiber, Spander	c, Pass	-
		8	Polypropylene, Polyester fiber, Spander	c, Pass	-
•		9	Polypropylene, Polyester fiber, Spander	c, Pass	-
		10	Polypropylene, Polyester fiber, Spander	c, Pass	-
		11	Polypropylene, Polyester fiber, Spander	c, Pass	-
		12	Polypropylene, Polyester fiber, Spander	c, Pass	-
		13	Polypropylene, Polyester fiber, Spander	c, Pass	-
		14	Polypropylene, Polyester fiber, Spander	c, Pass	-
		15	Polypropylene, Polyester fiber, Spander	c, Pass	-
		16	Polypropylene, Polyester fiber, Spander	c, Pass	-
		17	Polypropylene, Polyester fiber, Spander	c, Pass	-
		18	Polypropylene, Polyester fiber, Spander	c, Pass	-
		19	Polypropylene, Polyester fiber, Spande	c, Pass	-
		20	Polypropylene, Polyester fiber, Spander	c, Pass	.=
		21	Polypropylene, Polyester fiber, Spander	c, Pass	-
		22	Polypropylene, Polyester fiber, Spander	c, Pass	-
		23	Polypropylene, Polyester fiber, Spander	c, Pass	-
		24	Polypropylene, Polyester fiber, Spander	c, Pass	-
		25	Polypropylene, Polyester fiber, Spander	c, Pass	-
	i.	26	Polypropylene, Polyester fiber, Spander	c, Pass	-
		27	Polypropylene, Polyester fiber, Spander	c, Pass	-
		28	Polypropylene, Polyester fiber, Spander	c, Pass	-
		29	Polypropylene, Polyester fiber, Spander	ς, Pass	-

Verdict
-

30	Polypropylene, Polyester fiber, Spandex,	Pass	-
31	Polypropylene, Polyester fiber, Spandex,	Pass	-
32	Polypropylene, Polyester fiber, Spandex,	Pass	-

## Supplementary information:

- 1, Each specimen was conditioned at <u>21</u> °C and <u>85</u>% relative humidity for <u>4</u> h to bring them into equilibrium with atmosphere prior to testing.
- 2, The description of target area tested: the centre of the specimen
- 3, Any technique used to enhance visual detection of synthetic blood: cotton absorbent swab
- 4, The temperature and relative humidity for testing:  $\underline{\phantom{a}}$  21  $^{\circ}$ C and  $\underline{\phantom{a}}$  80  $^{\circ}$  %
- 5, Description of any pre-treatment techniques used: \\_\

5.2.5	TABLE: Mi	: Microbial cleanliness (Bioburden)					
Batch/ lot no.:		Mask(under test) no.:	Weight of each mask (g)	Total bioburden per individual mask (CFU/g)	Remark	arks	
20060906		1	3.2	15.3	≤30		
	2	3.1	12.9	≤30			
	3	3.2	14.4	≤30			
	4	3.1	15.2	≤30	-		
	5	3.1	13.2	≤30			

## Supplementary information:

The plates are incubated for 3 days at 30 °C and 7 days at (20 to 25) °C for TSA and SDA plates respectively.

#### **END OF TEST REPORT**